

## Service Temperature

-40° F to 180° F

## Application and Tooling

Apply with conventional caulking equipment, filling joint completely. When temperature is below 40° F., application will be easier if sealant is warmed. When temperature of surface to be sealed exceeds 140° F., do not apply sealant until surface cools. A soap solution or a solvent such as Xylol may be used as a lubricant for tooling. Do not allow tooling agents to contaminate open joints.

**Painting:** Sealant may be painted after 24 hours. If using a relatively inflexible paint, allow sealant to cure for 3 days before painting. Geocel 2300 may be coated with any latex and most oil-base paints. Some paints may crack in dynamic joints. See paint manufacturer's specifications.

**Cleaning:** Remove Geocel 2300 from gun and tools before it cures. This may be done by scraping and use of solvents such as (lacquer thinner), Xylol, Toluol or chlorinated solvents. Cured materials may be removed by cutting with sharp tools. Observe manufacturer's precautions when using toxic or flammable solvents.

## Storage Life

One year

## Precautions

Apply with adequate ventilation. Avoid eye contact. As supplied, product may be harmful or fatal if swallowed; do not induce vomiting, contact a physician immediately. Although the solvent blend is considered mild, some people may experience sensitivity to it.

## Limited Warranty

Geocel Corporation warrants that the product is manufactured according to their published standards and that the product is free from defects. The company guarantees for five years from the date of manufacture that Geocel 2300 will not crack due to normal expansion and contraction and that it will not lose its adhesion or cohesion. Geocel Corporation will, at its option, either refund the purchase price of, or provide replacement for, that portion of the Geocel 2300 which fails to perform in accordance with this warranty. Such refund or replacement will constitute the limit of Geocel's liability and obligation for any such failure. Geocel Corporation will not be liable or obligated otherwise for any loss or damage, arising directly or indirectly, from Geocel 2300 or the use or failure thereof, whether based on breach of warranty or negligence.

## Maintenance

No maintenance should be required. If the sealant is damaged either remove bead and reseal with Geocel 2300, or apply additional Geocel 2300 over the damaged area.

## Technical Services

Geocel representatives throughout the U.S. are available to provide technical assistance. Geocel's in house technical staff and laboratory facilities are equipped to respond to specific requests for further information and/or applications testing.

Joint Size	Linear Feet
1/4" x 1/4"	29.2
1/4" x 3/8"	19.4
1/4" x 1/2"	14.5
1/2" x 3/8"	9.7
1/2" x 1/2"	7.3
3/4" x 1/2"	4.8